

EPOCON SP 980

High Range Water Reducing, Set Retarder, Super Plasticizer Concrete Admixture



DESCRIPTION

EPOCON SP 980 is a high range water reducing, early strength increasing super plasticizer concrete admixture. It can provide very high level of water reduction up to 15 to 20 % without loss of workability or to produce high quality concrete of reduced permeability with highly early strength

CHARACTERISTICS

EPOCON SP 980 is used for ready mix concrete and precast industry where high early compressive strength of the concrete is very important. It reduces mixing water (w/c ratio in concrete structure). It promotes excellent dispersion of the particles in cement resulting in a major improvement of the workability. It provides good wetting of fine-coarse aggregates, cement and mineral additives. It can be used under all weather conditions. It does not cause segregation. Free of Cl ions. It can be used with all types of cement. Prolongation of workability time depends on cement type and ambient temperature

APPLICATIONS

EPOCON SP 980 is used for cross-sections, ready mix concrete for early mold in projects and all types of concrete structures. It is used for producing prefabricated members, economical concrete, quality plasticizer concrete, and precast industry. It is used for providing stable concrete strength. It is used for increasing 16 hours and 28 days strength.

USAGE

EPOCON SP 980 is used as a plasticizer without any risks of segregation, for ready mix concrete and precast industry where high early strength is necessary. Mix cement (and pozzolanic materials), sand, aggregate and 50-70% of mixing water are mixed until a homogeneous mixture obtained. **EPOCON SP 980** is added the remaining mixing water and mixed until a homogeneous mixture and the desired workability obtained.

COMPATIBILITY

EPOCON SP 980 can be used in all types of Portland cement, sulfate resisting cement and supplementary cementitious materials. **EPOCON SP 980** should be dispensed directly into the mixer and should not be pre-mixed with other admixtures.

If other admixtures are to be used in concrete containing **EPOCON SP 980**, they must be dispensed separately.

TECHNICAL SPECIFICATION

Test Name	Average Result
Chemical Composition	Sulphonated naphthalene based
Form	Liquid (Homogeneous)
Colour	Brown
Specific Gravity @20°C	1.225 ± 0.01
pH	7 ± 1.5
Chloride content (%)	< 0.1
Freeze harm	Complete Stir or agitate the container before use
Freeze temperature	0°C
Boiling point	100°C
Odor	Mild odor
Toxicity	None
Flammability	None
Clean-up	Water
Fumes during treatment	Slight
Environmental Hazards	None
Air Entrainment	Up to 2.0% depending on dosage rate and concrete proportioning.



EPOCON SP 980

Ver 02/20

EPO GULF SPECIALITIES CO.

Kuwait, Amghara Industrial area

Block 4 Building 95 – 97 – 99

P.O box 12017 – Tel: +965 22272590

info@epogulf.com

WWW.EPOGULF.COM



EPO YAPI KIMYA CO.

Cement – Concrete Technology

Turkey, Istanbul, Tuzla, Orhanlı

Tel: +90 2165932294

info@epo.com.tr

EPOCON SP 980

High Range Water Reducing, Set Retarder, Super Plasticizer Concrete Admixture



CONSUMPTION

EPOCON SP 980 is used in a range of 0.60 Kg to 1.9 Kg/100Kg of the cementitious material weight (Depending on climatic conditions, proportioning and other components of the concrete)

REMARKS

Usage dosages stated here under were obtained in laboratory conditions; they may change depending on the characteristics of other components, ambient conditions and water/cement ratio. Therefore, it is recommended that designs and tests should be conducted at sites using preliminary mixture ratios.

RELEVANT STANDARDS

ASTM C 494 Type F/G, BS 5075 Part I, BS EN 934 Part 2 (TS EN 934-2), (EN 480-10)

PACKING

Plastic jerry can (30Kg), Drums (250Kg), Bulk (storage tanks can be provided for Bulk use)

SHELF LIFE

12 months indoors, without opening original package. The product should be stored in a cool, dry storage. Do not store at temperatures below 10°C or in direct sunlight.

TECHNICAL ASSISTANCE

EPO GULF SPECIALITIES; technical department with its highly trained and qualified Chemicals Marketing Advisory team provides a complete service in the field. Please consult your nearest service/sales department for assistance. Field services where provided, do not constitute any supervisory responsibilities.

TECHNICAL INFORMATION

Typical Engineering Data: The following data using **EPOCON SP 980** was developed under laboratory conditions and according to ASTM C 494/10a limits Type F/G.

Mix Design:

Cement content (OPC): 307 Kg/M³
Coarse aggregate: approx. 30 %
Fine aggregate: approx. 70 %
Admixture dosage: 1 %
Water/Cement Ratio: 0.52

Properties	Specification % of Control	EPOCON SP 980
Compressive Strength vs. Control 100% 3 days 7 days 28 days	125 % 115 % 110 %	> 130 % > 120 % > 110 %
Flexural Strength vs. Control 100% 7 days 28 days	100 % 100 %	> 105 % > 102 %

Properties	Control Mix	EPOCON SP 980
Setting Time Initial Setting Final Setting	240 min 495 min	430 min 562 min
Length Change ASTM C 157 @28 days	-0.025 %	-0.031 % Pass

SAFETY PRECAUTIONS

As with all construction chemical products, adequate precautions and care must be taken during usage and storage. Avoid direct contact with foodstuff, eyes, skin, and mouth. Keep away from children and animals. Any direct contact with skin, eyes, etc. should be washed thoroughly with clean running water and soap. Use proper safety wear, goggles, and mask, etc.

NOTICE

The information given in this publication is based on present state of our knowledge. Any recommendations and suggestions are made without guarantee since the conditions and procedures are beyond our control. Buyers and users should make their own assessment of our product under their own conditions and for their own requirements

EPO GULF SPECIALITIES CO.

Kuwait, Amghara Industrial area
Block 4 Building 95 – 97 – 99
P.O box 12017 – Tel: +965 22272590
info@epogulf.com

WWW.EPOGULF.COM



EPO YAPI KIMYA CO.

Cement – Concrete Technology
Turkey, Istanbul, Tuzla, Orhanli
Tel: +90 2165932294
info@epo.com.tr

EPOCON SP 980

Ver 02/20