

EPO BOND FD 1:1

Epoxy Based Fairing Coat, Adhesive and Repair Putty



DESCRIPTION

EPO BOND FD 1:1 is thixotropic solvent free, two component based on epoxy resins, graded fillers and thixotropic agents, specially formulated to meet a range of service temperatures from 25°C to 60°C. The base component is white coloured and the hardener is black to facilitate ease of mixing.

TYPICAL APPLICATIONS

EPO BOND FD 1:1 is designed for application to minor imperfections in concrete surfaces. It is suitable for application from a feather-edge to 5 mm, and can be used in the following situations:

- As a steel anchoring and cavity filler.
- Sealing of surface cracks in preparation for crack injection.
- General purpose bedding mortar and adhesive
- Highly recommended for repair of structures that will be permanently submerged in water, sea water like water intake areas in power plants etc.
- As an adhesive for bonding pre-fabricated concrete bridge segments.
- General re-profiling over large areas, up to 5 mm depth.

ADVANTAGES

- Easy to apply, Non – sag, can be applied to vertical surfaces and trowelled into blow holes.
- Paste like consistency.
- Excellent bonding to concrete, steel and metal surfaces.
- Cures and hardens without shrinkage, hardening is not affected by high humidity.
- Can be applied from feather edge to 5 mm thickness even on damp or wet substrates.
- Suitable for marine and buried applications.
- High chemical ,abrasion and impact resistance
- Manufactured in Kuwait for severe climatic conditions of the Middle East.

STANDARD COMPLIANCE

ASTM C 881 – Type 1 & 4, Grade 3 Class B & C.
Passes ASTM C 883 & ASTM C 884.

PRODUCT DATA

Form	Paste like consistency
Colour	Off-white/Grey
Packing	1. Part A : 1.5 Kg 2. Part B : 1.5 Kg 3.Full Pack(A+B) : 3 Kg Pails
Layer Thickness	1mm to 5mm
Consumption	2 Kg/m ² (for 1 mm)
Shelf life	12 months, indoor storing non-open packaging under controlled condition

TECHNICAL SPECIFICATION

Test Name	Standard	Average Result
Density @25°C	---	1.80 ± 0.1 Kg/Ltr
Working time	---	About 120 minutes at 20°C and about 90 minutes at 35°C
Bond Strength 2 days 14 days	ASTM C 882	12 ± 1 MPa 14 ± 1 MPa
Compressive Strength 1 day 3 days 7 days	ASTM D 695	32 ± 2 MPa 35 ± 2 MPa 42 ± 2 MPa
Compressive Modulus	ASTM D 695	1058 MPa
Water Absorption 24 Hours	ASTM D 570	0.03%
Linear Coefficient of shrinkage	ASTM D 351	0.190%
Tensile Strength	----	2.5 ± 1 MPa
Elongation	ASTM D 638	9.5 %
Viscosity @ 25°C	ASTM D 2196	2350 ± 200 cps
Gel time @ 25°C	ASTM C 881	35 ± 10 min
Thermal compatibility	ASTM C 884	No Failure
Consistency	ASTM C 881	2 min

APPLICATION PROCEDURE

SUBSTRATE PREPARATION

Steel surfaces should be cleaned, dry and sand blasted, concrete surfaces should be clean, dry and free from dust & laitance. Sand blasting or mechanical wire brushing may be necessary.

EPO BOND FD 1:1

Ver 03/20

EPO GULF SPECIALITIES CO.

Kuwait, Amghara Industrial area
Block 4 Building 95 – 97 – 99
P.O box 12017 – Tel: +965 22272590
info@epogulf.com

WWW.EPOGULF.COM



EPO YAPI KIMYA CO.

Cement – Concrete Technology
Turkey, Istanbul, Tuzla, Orhanli
Tel: +90 2165932294
info@epo.com.tr

EPO BOND FD 1:1

Epoxy Based Fairing Coat, Adhesive and Repair Putty



MIXING

EPO BOND FD 1:1 should be thoroughly mixed to produce a fully homogenous paste. The hardener and base components (Recommended to mix full packs) should be mixed thoroughly using a drill and paddle attachment not exceeding 400 rpm. Mixing part packs is not preferable, but in case of such need mixing ratios are varies depend up on products by volume or by weight. **EPO BOND FD 1:1** can be finished using water wet sponge, water wet trowel to obtain smooth finish before initial set.

APPLICATION

A variety of tools such as trowel, scrapper, filling knife can be used. After mixing, material can be taken directly from the can, or sub divided into spot boards for individual applicators.

- As an adhesive for bonding pre – cast concrete segments, glove protected hands can also be used to apply **EPO BOND FD 1:1** to one or both of the surfaces.
- **EPO BOND FD**, when used as a fairing coat can be over coated with all **EPO** Range of epoxy coatings within 8 to 24 hrs of operation.

CLEANING

Use **EPO SOLVENT** for cleaning uncured **EPO BOND FD**, cured material can only be removed mechanically.

LIMITATIONS

- Do not mix part packs under any circumstances.
- **EPO BOND FD 1:1** should not be exposed to moving water during application.
- Exposure to heavy rainfall prior to final set may result in surface scour.
- If any doubt arises concerning temperature or substrate condition, consult the **EPO GULF SPECIALITIES TECHNICAL DEPARTMENT**.

PRECAUTIONS

HEALTH AND SAFETY

EPO BOND FD 1:1 and **EPO SOLVENT** should not come in contact with skin or eyes, or be swallowed. Ensure adequate ventilation and avoid inhalation of vapors. Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye/face protection.

If working in confined areas, suitable respiratory protective equipment must be used. The use of barrier creams provides additional skin protection. Should accidental skin contact occur, remove immediately with a resin removing cream followed by soap and water. Do not use solvent. In case of contact with eye, rinse immediately with plenty of clean water and seek medical advice. If swallowed seek medical attention immediately - do not induce vomiting.

FIRE

EPO BOND FD 1:1 is non-flammable.

EPO SOLVENT is flammable. Keep away from sources of ignition. No smoking. In the event of fire extinguish with CO₂ or foam. Do not use a water jet.



EPO BOND FD 1:1

Ver 03/20

EPO GULF SPECIALITIES CO.

Kuwait, Amghara Industrial area
Block 4 Building 95 – 97 – 99
P.O box 12017 – Tel: +965 22272590
info@epogulf.com

WWW.EPOGULF.COM



EPO YAPI KIMYA CO.

Cement – Concrete Technology
Turkey, Istanbul, Tuzla, Orhanlı
Tel: +90 2165932294
info@epo.com.tr