

EPOCON PLUS 50

PCE Based High Range Hyper Plasticizer, Self-Compacting Concrete Admixture



EPOCON PLUS 50 should not be used in conjunction with Naphthalene or Melamine based admixtures and remnants of these admixtures should be hosed down from storage tank and ducts with large quantity of water before using it for EPOCON PLUS 50.

DESCRIPTION

EPOCON PLUS 50 is high performance, high water reducing, self-compacting hyper plasticizer based on PCE technology, specially developed for applications in the ready mixed and precast concrete industries where the high strength durability and workability performance is required.

Super plasticizing action of **EPOCON PLUS 50** is different than conventional super plasticizers based on sulfonated melamine and naphthalene formaldehyde condensate, which create electrostatic repulsion of particles. **EPOCON PLUS 50** initially create the same electrostatic repulsion and further stabilizers the mixes due to static repulsion of long lateral chains linked to the polymer backbone.

CHARACTERISTICS

EPOCON PLUS 50 has been developed as a solution for applications in the premixed concrete industries where the highest performance and durability is required. It enables very low w/c ratios to be produced in the concrete without segregation or bleeding and slump retention is increased. It improves concrete surface finish and texture. **EPOCON PLUS 50** is a new generation hyper plasticizer concrete admixture, free of chlorides.

APPLICATIONS

Due to its excellent dispersion properties, **EPOCON PLUS 50** allows the production of high early and high ultimate strength concrete, increasing slump retention especially important for the premixed concrete. It is used for bridges, viaducts, turbo generators, the raft foundation of structures such as harbors, industrial grounds, airports, on the structures that concrete exposed to the corrosive effects and bridge beams with narrow sections.

USAGE

Mix cement (and pozzolanic materials), sand, fly ash, aggregate and 50-70 % of mixing water are mixed until a homogeneous consistency is obtained. **EPOCON PLUS 50** is added to the remaining mixing water and mixed until a homogeneous consistency and required workability are obtained.

COMPATIBILITY

EPOCON PLUS 50 can be used in all types of Portland cement, sulfate resisting cement and supplementary cementitious materials. **EPOCON PLUS 50** should be dispensed directly into the mixer and should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing **EPOCON PLUS 50**, they must be dispensed separately.

TECHNICAL SPECIFICATION

Test Name	Average Result
Chemical Composition	Polycarboxylic ether based
Form	Liquid
Colour	Light Brown
Specific Gravity @20°C	1.125 ± 0.01
pH	6 ± 2
Chloride content (%)	< 0.1
Freeze harm	Complete Stir or agitate the container before use
Freeze temperature	0°C
Boiling point	100°C
Odor	Mild odor
Toxicity	None
Flammability	None
Clean-up	Water
Fumes during treatment	Slight
Environmental Hazards	None
Air Entrainment	Up to 2.2% depending on dosage rate and concrete proportioning.



FEATURES / BENEFITS

- When used to produce “flowing” concrete, significantly reduces concrete placement time and cost.

EPO GULF SPECIALITIES CO.
Kuwait, Amghara Industrial area
Block 4 Building 95 – 97 – 99
P.O box 12017 – Tel: +965 22272590
info@epogulf.com

WWW.EPOGULF.COM



EPO YAPI KIMYA CO.
Cement – Concrete Technology
Turkey, Istanbul, Tuzla, Orhanli
Tel: +90 2165932294
info@epo.com.tr

EPOCON PLUS 50

Ver 01/22

EPOCON PLUS 50

PCE Based High Range Hyper Plasticizer, Self-Compacting Concrete Admixture



- Reduces segregation and bleeding in the plastic concrete.
- Produces “flowing” concrete with controlled delay of slump loss and workability.
- Greatly reduces water requirements.
- Enables under water concreting and Anti wash-out properties.
- Reduces cracking permeability of hardened concrete.
- Enhance the freezing - thaw cycle of hardened concrete.
- Improve concrete’s durability, physical and mechanical properties.
- Improve concrete corrosion resistance against chlorides, sulfates and aggressive environment compounds.

CONSUMPTION

EPOCON PLUS 50 is used in a range of 0.80 Kg to 2.5 Kg/100Kg of the cementitious material weight (Dosage varies depending on climatic conditions, proportioning and other components of concrete)

REMARKS

Use of dosages stated here under were obtained in laboratory conditions; they may change depending on the characteristics of other components, ambient conditions and water/cement ratio. Therefore, it is recommended that designs and tests should be conducted at sites using preliminary mixture ratios. **EPOCON PLUS 50** is not suitable to be used with any of the **EPOCON** series **SNF** based products.

RELEVANT STANDARDS

ASTM C494 Type G and **ASTM C1017 Type II** Plasticizing and retarding.

PACKING

IBC (1000 Ltr), Bulk

SHELF LIFE

12 months from the date of manufacturing.

STORAGE CONDITION

Store indoor at a temperature between +5°C to +45°C. If frozen agitate thoroughly before use. Protect from direct sunlight.

SAFETY PRECAUTIONS

As with all construction chemical products, adequate precautions and care must be taken during usage and storage. Avoid direct contact with foodstuff, eyes, skin, and mouth. Keep away from children and animals. Any direct contact with skin, eyes, etc. should be washed thoroughly with clean running water and soap. Use proper safety wear, goggles, and mask, etc.

TECHNICAL ASSISTANCE

EPO GULF SPECIALITIES; technical department with its highly trained and qualified Chemicals Marketing Advisory team provides a complete service in the field. Please consult your nearest service/sales department for assistance. Field services where provided, do not constitute any supervisory responsibilities.

NOTICE

The information given in this publication is based on present state of our knowledge. Any recommendations and suggestions are made without guarantee since the conditions and procedures are beyond our control. Buyers and users should make their own assessment of our product under their own conditions and for their own requirements

EPOCON PLUS 50

Ver 01/22

EPO GULF SPECIALITIES CO.

Kuwait, Amghara Industrial area
Block 4 Building 95 – 97 – 99
P.O box 12017 – Tel: +965 22272590
info@epogulf.com

WWW.EPOGULF.COM



EPO YAPI KIMYA CO.

Cement – Concrete Technology
Turkey, Istanbul, Tuzla, Orhanlı
Tel: +90 2165932294
info@epo.com.tr